

المخامات الدقيقة

ZF
analyse chimique (état sec)

ELEMENT	%
Fe	64,50
Fe ⁺⁺	0,50
SiO ₂	6,00
Al ₂ O ₃	1,00
P	0,05
LOI	0,60
H ₂ O	1,50

Grain gradation

< 0,150	: 32 %
> 8 mm	: 8.00 %
D50	= 1,25 mm
D80	= 6,00 mm

TZFC
Chimical test

ELEMENT	%
Fe	62,00
Fe ⁺⁺	1,15
SiO ₂	8,80
Al ₂ O ₃	0,90
P	0,070
LOI	0,70
H ₂ O	1,50

Grain gradation

< 0,150 mm	: 31.5 %
> 8 mm	: 6.00 %
D50	= 0,560 mm
D80	= 4,500 mm

XFC
Chimical test

ELEMENT	%
Fe	58,00
Fe ⁺⁺	1,00
SiO ₂	13,50
Al ₂ O ₃	1,00
P	0,075
LOI	0,70
H ₂ O	1,50

Grain gradation

< 0,150 mm	: 35.00 %
> 8 mm	: 8.00 %
D50	= 0,480 mm
D80	= 3,00 mm